RECEIVED CENTRAL FAX CENTER

FEB 1 2 2008

Appl. No. 10/594,784 Response Dated February 12, 2008 Reply to Office Action of November 14, 2007

The Pending Claims:

This listing will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Claim 1 (Previously presented): An acrylic elastomer composition, which comprises a carboxyl

group-containing acrylic elastomer, (A) a vulcanizing agent of polyvalent amine compound, and (B)

a thiazole-based compound selected from 2-mercaptobenzothiazole, or its zinc salt, or dibenzothiazyl

disulfide.

Claim 2 (Original): An acrylic elastomer composition according to Claim 1, wherein the carboxyl

group-containing acrylic elastomer is an aliphatic unsaturated dicarboxylic acid monoalkyl ester-

copolymerized acrylic elastomer.

Claim 3 (Original): An acrylic elastomer composition according to Claim 1, wherein 0.05-10 parts

by weight of the thiazole-based compound is contained on the basis of 100 parts by weight of the

carboxyl group-containing acrylic elastomer.

-2-

PAGE 3/16 * RCVD AT 2/12/2008 4:52:18 PM [Eastern Standard Time] * SVR:USPTO-EFXRF-6/4 * DNIS:2738300 * CSID: * DURATION (mm-ss):04-12

FEB 12 2008 16:57 FR TO 915712738300 P.04/16

Appl. No. 10/594,784 Response Dated February 12, 2008

Reply to Office Action of November 14, 2007

Claim 4 (Original): An acrylic elastomer composition according to Claim 2, wherein 0.05-10 parts

by weight of the thiazole-based compound is contained on the basis of 100 parts by weight of the

carboxyl group-containing acrylic elastomer.

Claim 5 (Original): An acrylic elastomer composition according to Claim 1, wherein the thiazole-

based compound is used together with an amine-based or phenol-based antioxidant.

Claim 6 (Original): An acrylic elastomer composition according to Claim 2, wherein the thiazole-

based compound is used together with an amine-based or phenol-based antioxidant.

Claim 7 (Previously presented): An acrylic elastomer composition according to Claim 1, wherein

0.1-5 parts by weight of a vulcanizing agent of polyvalent amine compound is further contained on

the basis of 100 parts by weight of the carboxyl group-containing acrylic elastomer.

Claim 8 (Original): An acrylic elastomer vulcanization-molded article, vulcanization-molded from

an acrylic elastomer composition according to Claim 1.

Claim 9 (Canceled)

FEB 12 2008 16:57 FR TO 915712738300 P.05/16

Appl. No. 10/594,784 Response Dated February 12, 2008 Reply to Office Action of November 14, 2007

Claim 10 (Original): An acrylic elastomer vulcanization-molded article according to Claim 8, which has parts in a wall thickness of not more than 30mm.

Claim 11 (Canceled)

Claim 12 (Original): An acrylic elastomer vulcanization-molded article according to Claim 10, wherein the vulcanization-molded article having parts in a wall thickness of not more than 30mm is a gasket or O ring.

Claim 13 (Canceled)